



Standard Specification for Titanium and Titanium Alloy Strip, Sheet, and Plate¹

This standard is issued under the fixed designation B265; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers annealed titanium and titanium alloy strip, sheet, and plate as follows:

- 1.1.1 *Grade 1*—UNS R50250. Unalloyed titanium,
- 1.1.2 *Grade 2*—UNS R50400. Unalloyed titanium,
 - 1.1.2.1 *Grade 2H*—UNS R50400. Unalloyed titanium (Grade 2 with 58 ksi (400 MPa) minimum UTS),
- 1.1.3 *Grade 3*—UNS R50550. Unalloyed titanium,
- 1.1.4 *Grade 4*—UNS R50700. Unalloyed titanium,
- 1.1.5 *Grade 5*—UNS R56400. Titanium alloy (6 % aluminum, 4 % vanadium),
- 1.1.6 *Grade 6*—UNS R54520. Titanium alloy (5 % aluminum, 2.5 % tin),
- 1.1.7 *Grade 7*—UNS R52400. Unalloyed titanium plus 0.12 to 0.25 % palladium,
 - 1.1.7.1 *Grade 7H*—UNS R52400. Unalloyed titanium plus 0.12 to 0.25 % palladium (Grade 7 with 58 ksi (400 MPa) minimum UTS),
- 1.1.8 *Grade 9*—UNS R56320. Titanium alloy (3.0 % aluminum, 2.5 % vanadium),
- 1.1.9 *Grade 11*—UNS R52250. Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.10 *Grade 12*—UNS R53400. Titanium alloy (0.3 % molybdenum, 0.8 % nickel),
- 1.1.11 *Grade 13*—UNS R53413. Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.12 *Grade 14*—UNS R53414. Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.13 *Grade 15*—UNS R53415. Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.14 *Grade 16*—UNS R52402. Unalloyed titanium plus 0.04 to 0.08 % palladium,
 - 1.1.14.1 *Grade 16H*—UNS R52402. Unalloyed titanium plus 0.04 to 0.08 % palladium (Grade 16 with 58 ksi (400 MPa) minimum UTS),

1.1.15 *Grade 17*—UNS R52252. Unalloyed titanium plus 0.04 to 0.08 % palladium,

1.1.16 *Grade 18*—UNS R56322. Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.04 to 0.08 % palladium,

1.1.17 *Grade 19*—UNS R58640. Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum),

1.1.18 *Grade 20*—UNS R58645. Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum) plus 0.04 % to 0.08 % palladium,

1.1.19 *Grade 21*—UNS R58210. Titanium alloy (15 % molybdenum, 3 % aluminum, 2.7 % niobium, 0.25 % silicon),

1.1.20 *Grade 23*—UNS R56407. Titanium alloy (6 % aluminum, 4 % vanadium with extra low interstitial elements, ELI),

1.1.21 *Grade 24*—UNS R56405. Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.04 % to 0.08 % palladium,

1.1.22 *Grade 25*—UNS R56403. Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.3 % to 0.8 % nickel and 0.04 % to 0.08 % palladium,

1.1.23 *Grade 26*—UNS R52404. Unalloyed titanium plus 0.08 to 0.14 % ruthenium,

1.1.23.1 *Grade 26H*—UNS R52404. Unalloyed titanium plus 0.08 to 0.14 % ruthenium (Grade 26 with 58 ksi (400 MPa) minimum UTS),

1.1.24 *Grade 27*—UNS R52254. Unalloyed titanium plus 0.08 to 0.14 % ruthenium,

1.1.25 *Grade 28*—UNS R56323. Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.08 to 0.14 % ruthenium,

1.1.26 *Grade 29*—UNS R56404. Titanium alloy (6 % aluminum, 4 % vanadium with extra low interstitial elements, ELI) plus 0.08 to 0.14 % ruthenium,

1.1.27 *Grade 30*—UNS R53530. Titanium alloy (0.3 % cobalt, 0.05 % palladium),

1.1.28 *Grade 31*—UNS R53532. Titanium alloy (0.3 % cobalt, 0.05 % palladium),

1.1.29 *Grade 32*—UNS R55111. Titanium alloy (5 % aluminum, 1 % tin, 1 % zirconium, 1 % vanadium, 0.8 % molybdenum),

1.1.30 *Grade 33*—UNS R53442. Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.01 on Titanium.

Current edition approved Nov. 1, 2015. Published December 2015. Originally approved in 1952. Last previous edition approved in 2013 as B265 – 13a^ε. DOI: 10.1520/B0265-15.

² For ASME Boiler and Pressure Vessel Code applications see related Specifications SB-265 in Section II of that Code.

1.1.31 *Grade 34*—UNS R53445. Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),

1.1.32 *Grade 35*—UNS R56340. Titanium alloy (4.5 % aluminum, 2 % molybdenum, 1.6 % vanadium, 0.5 % iron, 0.3 % silicon),

1.1.33 *Grade 36*—UNS R58450. Titanium alloy (45 % niobium),

1.1.34 *Grade 37*—UNS R52815. Titanium alloy (1.5 % aluminum),

1.1.35 *Grade 38*—UNS R54250. Titanium alloy (4 % aluminum, 2.5 % vanadium, 1.5 % iron), and

1.1.36 *Grade 39*—UNS R53390. Titanium alloy (0.25 % iron, 0.4 % silicon).

NOTE 1—H grade material is identical to the corresponding numeric grade (that is, Grade 2H = Grade 2) except for the higher guaranteed minimum UTS, and may always be certified as meeting the requirements of its corresponding numeric grade. Grades 2H, 7H, 16H, and 26H are intended primarily for pressure vessel use.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:³

E8 Test Methods for Tension Testing of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E290 Test Methods for Bend Testing of Material for Ductility

E539 Test Method for Analysis of Titanium Alloys by X-Ray Fluorescence Spectrometry

E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method

E1941 Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis

E2371 Test Method for Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)

E2626 Guide for Spectrometric Analysis of Reactive and Refractory Metals

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 Any product 0.187 in. (4.75 mm) and under in thickness and less than 24 in. (610 mm) in width is classified as strip; products 0.187 in. (4.75 mm) and under in thickness and 24 in. (610 mm) or more in width are classified as sheet; any product over 0.187 in. (4.75 mm) in thickness and over 10 in. (254 mm) in width is classified as plate.

4. Ordering Information

4.1 Orders for materials under this specification shall include the following information as applicable:

4.1.1 Grade number (Section 1),

4.1.2 Product limitations (Section 3),

4.1.2.1 For sheet specify cold or hot rolled. If not specified cold tolerances are the default.

(a) Cold rolled sheet tolerances are in Table 1, Table 2, and Table 3.

(b) Hot rolled sheet tolerances are in Table 1, Table 4, Table 5, and Table 6.

4.1.3 Special mechanical properties (Table 7),

4.1.4 Marking (Section 16),

4.1.5 Finish (Section 8),

4.1.6 Packaging (Section 16),

4.1.7 Additional required reports (Section 15), and

4.1.8 Disposition of rejected material (Section 14).

TABLE 1 Permissible Variations in Thickness of Titanium Sheet

Specified Thickness, in. (mm)	Permissible Variations in Thickness, Plus and minus, in. (mm)		Permissible Variations in Thickness Plus and minus, in. (mm) For hot rolled sheet	
	For cold rolled sheet			
			Width to 84 in. (2134 mm), incl	Width Over 84 in. (2134 mm)
0.146 to 0.1875 (3.71 to 4.76), excl	0.014 (0.36)		0.025 (0.64)	0.028 (0.71)
0.131 to 0.145 (3.33 to 3.68)	0.012 (0.31)		0.022 (0.558)	0.028 (0.71)
0.115 to 0.130 (2.92 to 3.30)	0.010 (0.25)		0.020 (0.508)	...
0.099 to 0.114 (2.51 to 2.90)	0.009 (0.23)		...	...
0.084 to 0.098 (2.13 to 2.49)	0.008 (0.20)		...	...
0.073 to 0.083 (1.85 to 2.11)	0.007 (0.18)		...	...
0.059 to 0.072 (1.50 to 1.83)	0.006 (0.15)		...	...
0.041 to 0.058 (1.04 to 1.47)	0.005 (0.13)		...	...
0.027 to 0.040 (0.69 to 1.02)	0.004 (0.10)		...	...
0.017 to 0.026 (0.43 to 0.66)	0.003 (0.08)		...	...
0.008 to 0.016 (0.20 to 0.41)	0.002 (0.05)		...	...
0.006 to 0.007 (0.15 to 0.18)	0.0015 (0.04)		...	...
0.005 (0.13)	0.001 (0.03)		...	...

TABLE 2 Permissible Variations in Width and Length of Cold Rolled Titanium Sheet

Specified Width, in. (mm), for Thicknesses Under $\frac{3}{16}$ in.	Permissible Variations in Width, in. (mm)
24 to 48 (610 to 1220), excl	$+\frac{1}{16}$ (+1.60), -0
48 (1220) and over	$+\frac{1}{8}$ (+3.20), -0
Specified Length, ft (m)	Permissible Variations in Length, in. (mm)
Up to 10 (3)	$+\frac{1}{4}$ (+6.35), -0
Over 10 to 20 (3 to 6)	$+\frac{1}{2}$ (+12.7), -0

TABLE 3 Permissible Variations in Weight of Cold Rolled Titanium Sheet

The actual weight of any one item of an ordered thickness and size in any finish is limited in overweight by the following tolerance:

Any item of five sheets or less, or any item estimated to weigh 200 lb (91 kg) or less, may actually weigh as much as 10 % over the estimated weight.

Any item of more than five sheets and estimated to weigh more than 200 lb may actually weigh as much as $7\frac{1}{2}$ % over the estimated weight.

There is no under tolerance in weight for titanium sheets, under tolerance being restricted by the permissible thickness variations.

Only random (or mill size) sheets may be ordered on a square foot basis, and the number of square feet shipped may exceed the number ordered by as much as 5 %.

TABLE 4 Permissible Variations in Width and Length of Hot Rolled Titanium Sheet

Specified Length, in. (mm)	Specified Width, in. (mm)	Permissible Variations in. (mm)	
		Width	Length
Under 120 (3048)	Under 60 (1524)	$+\frac{5}{8}$ (15.88), +0	$+\frac{3}{4}$ (19.05), 0
	60 to 84 (1524 to 2134), excl	$+\frac{1}{16}$ (17.46), +0	$+\frac{7}{8}$ (22.23), 0
	84 to 108 (2134 to 2743), excl	$+\frac{3}{4}$ (19.05), +0	+1 (25.40), 0
120 to 240 (3048 to 6096), excl	Under 60 (1524)	$+\frac{5}{8}$ (15.88), +0	+1 (25.40), 0
	60 to 84 (1524 to 2134), excl	$+\frac{3}{4}$ (19.05), +0	+1 (25.40), 0
	84 to 108 (2134 to 2743), excl	$+\frac{13}{16}$ (20.64), +0	$+1\frac{1}{8}$ (28.58), 0
240 to 360 (6098 to 9144), excl	Under 60 (1524)	$+\frac{5}{8}$ (15.88), +0	$+1\frac{1}{4}$ (31.75), 0
	60 to 84 (1524 to 2134), excl	$+\frac{3}{4}$ (19.05), +0	$+1\frac{1}{4}$ (31.75), 0
	84 to 108 (2134 to 2743), excl	$+\frac{13}{16}$ (20.64), +0	$+1\frac{1}{4}$ (31.75), 0
	Under 60 (1524)	$+\frac{1}{16}$ (17.46), +0	$+1\frac{3}{8}$ (34.93), 0
360 to 480 (9144 to 12192) and over	60 to 84 (1524 to 2134), excl	$+\frac{3}{4}$ (19.05), +0	$+1\frac{1}{2}$ (38.10), 0
	84 to 108 (2134 to 2743), excl	$+\frac{13}{16}$ (20.64), +0	$+1\frac{1}{2}$ (38.10), 0

TABLE 5 Permissible Variations in Weight of Hot Rolled Titanium Sheet

The actual weight of any one item or an order's thickness and size in any finish is limited in overweight by as much as 20 %.

5. Chemical Composition

5.1 The grades of titanium and titanium alloy metal covered by this specification shall conform to the chemical composition requirements prescribed in [Table 8](#).

5.1.1 The elements listed in [Table 8](#) are intentional alloy additions or elements which are inherent to the manufacture of titanium sponge, ingot or mill product.

5.1.1.1 Elements other than those listed in [Table 8](#) are deemed to be capable of occurring in the grades listed in [Table 8](#) by and only by way of unregulated or unanalyzed scrap additions to the ingot melt. Therefore, product analysis for elements not listed in [Table 8](#) shall not be required unless specified and shall be considered to be in excess of the intent of this specification.

5.1.2 Elements intentionally added to the melt must be identified, analyzed, and reported in the chemical analysis.

5.2 When agreed upon by producer and purchaser and requested by the purchaser in his written purchase order, chemical analysis shall be completed for specific residual elements not listed in this specification.

5.3 *Product Analysis*—Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations between laboratories in the measurement of chemical content. The manufacturer shall not ship material that is outside the limits specified in [Table 8](#) for the applicable grade. Product analysis limits shall be as specified in [Table 9](#).

5.4 At least two samples for chemical analysis shall be tested to determine chemical composition. Samples shall be taken from the ingot or the extremes of the product to be analyzed.

6. Mechanical Properties

6.1 Material supplied under this specification shall conform to the mechanical property requirements given in [Table 7](#) for the grade specified.

6.2 Tension testing specimens are to be machined and tested in accordance with Test Methods [E8](#). Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min through the specified yield strength, and then increasing the rate so as to produce failure in approximately one additional minute.

6.3 For sheet and strip, the bend test specimen shall withstand being bent cold through an angle of 105° without fracture in the outside of the bent portion. The bend shall be made on a **radius** equal to that shown in [Table 7](#) for the applicable grade. The bends are to be made in accordance with Test Method [E290](#), using Method 1, Guided Bend Test described in paragraph 3.6, bent through 105°, and allowed to spring back naturally. The surface of the specimen must include the original material surface with no material removal or surface conditioning, except corners may be rounded to a maximum radius of 0.032 in. (0.8 mm). The width of the bend shall be at least 5 times the thickness. The test report shall, at minimum, indicate acceptable or unacceptable results.

7. Permissible Variations in Dimensions

7.1 Dimensional tolerances on titanium and titanium alloy material covered by this specification shall be as specified in [Tables 1-6](#) and [Tables 10-16](#), as applicable.

TABLE 6 Permissible Variations from a Flat Surface for Titanium Hot Rolled Sheet

Permissible Variations from a Flat Surface for Width or Length Given, in. (mm)									
Specified Thickness, in. (mm)	48 (1219) or Under	48, excl to 60 (1219 to 1524), excl	60 to 72, (1524 to 1829), excl	72 to 84 (1829 to 2134), excl	84 to 96 (2134 to 2438), excl	96 to 108 (2438 to 2743), excl	108 to 120 (2743 to 3048), excl	120 to 144 (3048 to 3658), excl	144 (3658) and Over
0.146 to 0.1875 (3.71 to 4.76)	3/4 (19.05)	1 1/16 (26.99)	1 1/4 (31.75)	1 3/8 (34.92)	1 5/8 (41.28)	1 5/8 (41.28)	1 7/8 (47.6)	2 (50.8)	2 1/4 (57.15)
0.131 to 0.145 (3.33 to 3.68)	3/4 (19.05)	1 1/16 (26.99)	1 1/4 (31.75)	1 3/8 (34.92)	1 5/8 (41.28)	1 5/8 (41.28)	1 7/8 (47.6)	2 (50.8)	2 1/8 (53.98)
0.115 to 0.130 (2.92 to 3.30)	3/4 (19.05)	1 1/16 (26.99)	1 1/4 (31.75)	1 3/8 (34.92)	1 5/8 (41.28)	1 5/8 (41.28)	1 7/8 (47.6)	2 (50.8)	2 1/8 (53.98)

NOTE 1—Variations in flatness apply to plates up to 15 ft (4.57 m) in length, or to any 15 ft of longer plates.

NOTE 2—If the longer dimension is under 36 in. (914 mm) the variation is not greater than 1/4 in. (6.35) mm.

NOTE 3—The shorter dimension specified is considered the width and the variation in flatness across the width does not exceed the tabular amount for that dimension.

NOTE 4—The maximum deviation from a flat surface does not customarily exceed the tabular tolerance for the longer dimension specified.

8. Finish

8.1 Titanium and titanium alloy sheet, strip, and plate shall be free of injurious external and internal imperfections of a nature that will interfere with the purpose for which it is intended. Annealed material may be furnished as descaled, as sandblasted, or as ground, or both sandblasted and ground. If shipped as descaled, sandblasted, or ground, the manufacturer shall be permitted to remove minor surface imperfections by spot grinding if such grinding does not reduce the thickness of the material below the minimum permitted by the tolerance for the thickness ordered.

9. Sampling for Chemical Analysis

9.1 Samples for chemical analysis shall be representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its great affinity for elements such as oxygen, nitrogen, and hydrogen. Therefore, in cutting samples for analysis, the operation should be carried out insofar as possible in a dust-free atmosphere. Chips should be collected from clean metal and tools should be clean and sharp. Samples for analysis should be stored in suitable containers.

10. Methods of Chemical Analysis

10.1 The chemical analysis shall normally be conducted using the ASTM standard test methods referenced in 2.1. Other industry standard methods may be used where the ASTM test methods in 2.1 do not adequately cover the elements in the material or by agreement between the producer and purchaser. Alternate techniques are discussed in Guide E2626.

11. Retests

11.1 If the results of any chemical or mechanical property test lot are not in conformance with the requirements of this specification, the lot may be retested at the option of the manufacturer. The frequency of the retest will double the initial number of tests. If the results of the retest conform to the specification, then the retest values will become the test values for certification. Only original conforming test results or the conforming retest results shall be reported to the purchaser. If the results for the retest fail to conform to the specification, the material will be rejected in accordance with Section 14.

12. Referee Test and Analysis

12.1 In the event of disagreement between the manufacturer and the purchaser on the conformance of the material to the requirements of this specification, a mutually acceptable referee shall perform the tests in question using the ASTM standard methods in 2.1. The referee's testing shall be used in determining conformance of the material to this specification.

13. Rounding-Off Procedure

13.1 For purposes of determining conformance with this specification, an observed or a calculated value shall be rounded off to the nearest "unit" in the last right-hand significant digit used in expressing the limiting value. This is in accordance with the round-off method of Practice E29.

14. Rejection

14.1 Material not conforming to the specification or to authorized modifications shall be subject to rejection. Unless otherwise specified, rejected material may be returned to the manufacturer at the manufacturer's expense, unless the purchaser receives, within three weeks of notice of rejection, other instructions for disposition.

15. Certification

15.1 The manufacturer shall supply at least one copy of the report certifying that the material supplied has been manufactured, inspected, sampled, and tested in accordance with the requirements of this specification and that the results of chemical analysis, tensile, and other tests meet the requirements of this specification for the grade specified. The report shall include results of all chemical analysis, tensile tests, and all other tests required by the specification.

16. Marking and Packaging

16.1 Marking:

16.1.1 *Identification*—Unless otherwise specified, each plate, sheet, and strip shall be marked in the respective location indicated below, with the number of this specification, heat number, manufacturer's identification, and the nominal thickness in inches. The characters shall be not less than 3/8 in. (9.52 mm) in height, shall be applied using a suitable marking fluid, and shall be capable of being removed with a hot alkaline

TABLE 7 Tensile Requirements^A

Grade	Tensile Strength, min		Yield Strength, 0.2 % Offset				Elongation in 2 in. or 50 mm, min, %	Bend Test (Radius of Mandrel) ^F	
	ksi	MPa	min		max			Under 0.070 in. (1.8 mm) in Thickness	0.070 to 0.187 in. (1.8–4.75 mm) in Thickness
			ksi	MPa	ksi	MPa			
1	35	240	20	138	45	310	24	1.5 <i>T</i>	2 <i>T</i>
2	50	345	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i>
2H ^{C,D}	58	400	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i> †
3	65	450	55	380	80	550	18	2 <i>T</i>	2.5 <i>T</i>
4	80	550	70	483	95	655	15	2.5 <i>T</i>	3 <i>T</i>
5	130	895	120	828	...	...	10 ^E	4.5 <i>T</i>	5 <i>T</i>
6	120	828	115	793	...	...	10 ^E	4 <i>T</i>	4.5 <i>T</i>
7	50	345	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i>
7H ^{C,D}	58	400	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i> †
9	90	620	70	483	...	...	15 ^F	2.5 <i>T</i>	3 <i>T</i>
11	35	240	20	138	45	310	24	1.5 <i>T</i>	2 <i>T</i>
12	70	483	50	345	...	...	18	2 <i>T</i>	2.5 <i>T</i>
13	40	275	25	170	...	...	24	1.5 <i>T</i>	2 <i>T</i>
14	60	410	40	275	...	...	20	2 <i>T</i>	2.5 <i>T</i>
15	70	483	55	380	...	...	18	2 <i>T</i>	2.5 <i>T</i>
16	50	345	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i>
16H ^{C,D}	58	400	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i> †
17	35	240	20	138	45	310	24	1.5 <i>T</i>	2 <i>T</i>
18	90	620	70	483	...	...	15 ^F	2.5 <i>T</i>	3 <i>T</i>
19 ^{G,H}	115	793	110	759	...	...	15	3 <i>T</i>	3 <i>T</i>
20 ^{G,H}	115	793	110	759	...	...	15	3 <i>T</i>	3 <i>T</i>
21 ^{G,H}	115	793	110	759	...	...	15	3 <i>T</i>	3 <i>T</i>
23	120	828	110	759	...	...	10	4.5 <i>T</i>	5 <i>T</i>
24	130	895	120	828	...	...	10	4.5 <i>T</i>	5 <i>T</i>
25	130	895	120	828	...	...	10	4.5 <i>T</i>	5 <i>T</i>
26	50	345	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i>
26H ^{C,D}	58	400	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i> †
27	35	240	20	138	45	310	24	1.5 <i>T</i>	2 <i>T</i>
28	90	620	70	483	...	...	15	2.5 <i>T</i>	3 <i>T</i>
29	120	828	110	759	...	...	10	4.5 <i>T</i>	5 <i>T</i>
30	50	345	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i>
31	65	450	55	380	80	550	18	2 <i>T</i>	2.5 <i>T</i>
32	100	689	85	586	...	...	10 ^E	3.5 <i>T</i>	4.5 <i>T</i>
33	50	345	40	275	65	450	20	2 <i>T</i>	2.5 <i>T</i>
34	65	450	55	380	80	550	18	2 <i>T</i>	2.5 <i>T</i>
35	130	895	120	828	...	...	5	8 <i>T</i>	8 <i>T</i>
36	65	450	60	410	95	655	10	4.5 <i>T</i>	5 <i>T</i>
37	50	345	31	215	65	450	20	2 <i>T</i>	2.5 <i>T</i>
38	130	895	115	794	...	...	10	4 <i>T</i>	4.5 <i>T</i>
39	75	515	60	410	90	620	20	2 <i>T</i>	2.5 <i>T</i>

^A Minimum and maximum limits apply to tests taken both longitudinal and transverse to the direction of rolling. Mechanical properties for conditions other than annealed or plate thickness over 1 in. (25 mm) may be established by agreement between the manufacturer and the purchaser.

^B Bend to **Radius** of Mandrel, T equals the thickness of the bend test specimen. Bend tests are not applicable to material over 0.187 in. (4.75 mm) in thickness.

^C Material is identical to the corresponding numeric grade (that is, Grade 2H = Grade 2) except for the higher guaranteed minimum UTS, and may always be certified as meeting the requirements of its corresponding numeric grade. Grade 2H, 7H, 16H, and 26H are intended primarily for pressure vessel use.

^D The H grades were added in response to a user association request based on its study of over 5200 commercial Grade 2, 7, 16, and 26 test reports, where over 99 % met the 58 ksi minimum UTS.

^E For Grades 5, 6 and 32 the elongation on materials under 0.025 in. (0.635 mm) in thickness may be obtained only by negotiation.

^F Elongation for continuous rolled and annealed (strip product from coil) for Grade 9 and Grade 18 shall be 12 % minimum in the longitudinal direction and 8 % minimum in the transverse direction.

^G Properties for material in the solution treated condition.

^H Material is normally purchased in the solution treated condition. Therefore, properties for aged material shall be negotiated between manufacturer and purchaser.

†Editorially corrected.

cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance. The characters shall be sufficiently stable to withstand ordinary handling.

16.1.2 Plate, flat sheet, and flat strip over 6 in. (152 mm) in width shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 in. (76 mm), the rows being spaced not more than 2 in. (51 mm) apart and alternately staggered. Heat numbers shall occur at least 3 times across the

width of the sheet and at intervals not greater than 2 ft (0.610 m) along the length. As an option, when permitted, each plate, sheet, or cut length strip may be marked in at least one corner with the number of this specification, heat number, manufacturer's identification, and the nominal thickness in inches or millimetres as required.

16.1.3 Flat strip 6 in. (152 mm) and under in width shall be marked near one end.



TABLE 8 Chemical Requirements

Composition, Weight Percent^{A,B,C,D,E}

Composition, Weight Percent ^{A,B,C,D,E}																												
Grade	UNS Number	Carbon, max.	Oxygen range or max.	Nitrogen, max.	Hydrogen, max.	Iron range or max.	Aluminum										Other Elements, max. each											
							Vanadium	Palladium	Ruthenium	Nickel	Molybdenum	Chromium	Cobalt	Zirconium	Niobium	Tin	Silicon	max. total										
1	R50250	0.08	0.18	0.03	0.015	0.20	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
2/2H	R50400	0.08	0.25	0.03	0.015	0.30	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
3	R50550	0.08	0.35	0.05	0.015	0.30	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
4	R50700	0.08	0.40	0.05	0.015	0.50	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
5	R56400	0.08	0.20	0.05	0.015	0.40	5.5-6.75	3.5-4.5	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
6	R54520	0.08	0.20	0.03	0.015	0.50	4.0-6.0	--	--	--	--	--	--	--	--	--	--	--	--	2.0-3.0	--	--	--	--	--	--	0.1	0.4
7/7H	R52400	0.08	0.25	0.03	0.015	0.30	--	--	0.12-0.25	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
9	R56320	0.08	0.15	0.03	0.015	0.25	2.5-3.5	2.0-3.0	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
11	R52250	0.08	0.18	0.03	0.015	0.20	--	--	0.12-0.25	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
12	R53400	0.08	0.25	0.03	0.015	0.30	--	--	--	--	--	--	0.6-0.9	0.2-0.4	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
13	R53413	0.08	0.10	0.03	0.015	0.20	--	--	--	0.04-0.06	--	--	0.4-0.6	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
14	R53414	0.08	0.15	0.03	0.015	0.30	--	--	--	0.04-0.06	--	--	0.4-0.6	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
15	R53415	0.08	0.25	0.05	0.015	0.30	--	--	--	0.04-0.06	--	--	0.4-0.6	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
16/16H	R52402	0.08	0.25	0.03	0.015	0.30	--	--	0.04-0.08	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
17	R52252	0.08	0.18	0.03	0.015	0.20	--	--	0.04-0.08	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
18	R56322	0.08	0.15	0.03	0.015	0.25	2.5-3.5	2.0-3.0	0.04-0.08	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
19	R58640	0.05	0.12	0.03	0.02	0.30	3.0-4.0	7.5-8.5	--	--	--	--	--	3.5-4.5	5.5-6.5	--	--	--	--	--	--	--	--	--	--	--	0.15	0.4
20	R58645	0.05	0.12	0.03	0.02	0.30	3.0-4.0	7.5-8.5	0.04-0.08	--	--	--	--	3.5-4.5	5.5-6.5	--	--	--	--	--	--	--	--	--	--	--	0.15	0.4
21	R58210	0.05	0.17	0.03	0.015	0.40	2.5-3.5	--	--	--	--	--	--	14.0-16.0	--	--	--	2.2-3.2	--	--	--	--	--	0.15-0.25	--	0.1	0.4	
23	R56407	0.08	0.13	0.03	0.0125	0.25	5.5-6.5	3.5-4.5	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
24	R56405	0.08	0.20	0.05	0.015	0.40	6.5-7.5	3.5-4.5	0.04-0.08	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
25	R56403	0.08	0.20	0.05	0.015	0.40	6.75	4.5-5.5	0.04-0.08	--	--	--	0.3-0.8	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
26/26H	R52404	0.08	0.25	0.03	0.015	0.30	--	--	--	0.08-0.14	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
27	R52254	0.08	0.18	0.03	0.015	0.20	--	--	--	0.08-0.14	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
28	R56323	0.08	0.15	0.03	0.015	0.25	2.5-3.5	2.0-3.0	--	0.08-0.14	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
29	R56404	0.08	0.13	0.03	0.0125	0.25	5.5-6.5	3.5-4.5	--	0.08-0.14	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
30	R53530	0.08	0.25	0.03	0.015	0.30	--	--	0.04-0.08	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
31	R53532	0.08	0.35	0.05	0.015	0.30	--	--	0.04-0.08	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4



TABLE 8 Continued

Composition, Weight Percent ^{A,B,C,D,E}																				
Grade	UNS Number	Carbon, max.	Oxygen range	Nitrogen, max.	Hydrogen, max.	Iron range or max.	Composition, Weight Percent ^{A,B,C,D,E}								Other Elements, max. each	Other Elements, max. total				
							Aluminum	Vanadium	Palladium	Ruthenium	Nickel	Molybdenum	Chromium	Cobalt			Zirconium	Niobium	Tin	Silicon
32	R55111	0.08	0.11	0.03	0.015	0.25	4.5-5.5	0.6-1.4	--	--	--	0.6-1.2	--	--	0.6-1.4	--	0.6-1.4	0.06-0.14	0.1	0.4
33	R53442	0.08	0.25	0.03	0.015	0.30	--	--	0.01-0.02	0.02-0.04	0.35-0.55	--	0.1-0.2	--	--	--	--	--	0.1	0.4
34	R53445	0.08	0.35	0.05	0.015	0.30	--	--	0.01-0.02	0.02-0.04	0.35-0.55	--	0.1-0.2	--	--	--	--	--	0.1	0.4
35	R56340	0.08	0.25	0.05	0.015	0.20-0.80	4.0-5.0	1.1-2.1	--	--	--	1.5-2.5	--	--	--	--	--	0.20-0.40	0.1	0.4
36	R58450	0.04	0.16	0.03	0.015	0.03	--	--	--	--	--	--	--	--	--	42.0-47.0	--	--	0.1	0.4
37	R52815	0.08	0.25	0.03	0.015	0.30	1.0-2.0	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4
38	R54250	0.08	0.20-0.30	0.03	0.015	1.2-1.8	3.5-4.5	2.0-3.0	--	--	--	--	--	--	--	--	--	--	0.1	0.4
39	R53390	0.08	0.15	0.03	0.015	0.15-0.40	--	--	--	--	--	--	--	--	--	--	--	0.30-0.50	0.1	0.4

^A At minimum, the analysis of samples from the top and bottom of the ingot shall be completed and reported for all elements listed for the respective grade in this table.

^B Final product hydrogen shall be reported. Ingot hydrogen need not be reported. Lower hydrogen may be obtained by negotiation with the manufacturer.

^C Single values are maximum. The percentage of titanium is determined by difference.

^D Other elements need not be reported unless the concentration level is greater than 0.1 % each, or 0.4 % total. Other elements may not be added intentionally. Other elements may be present in titanium or titanium alloys in small quantities and are inherent to the manufacturing process. In titanium these elements typically include aluminum, vanadium, tin, chromium, molybdenum, niobium, zirconium, hafnium, bismuth, ruthenium, palladium, yttrium, copper, silicon, cobalt, tantalum, nickel, boron, manganese, and tungsten.

^E The purchaser may, in the written purchase order, request analysis for specific elements not listed in this specification.

TABLE 9 Permissible Variations in Product Analysis

Element	Product Analysis Limits, max or Range, %	Permissible Variation in Product Analysis
Aluminum	0.5 to 2.5	±0.20
Aluminum	2.5 to 6.75	±0.40
Carbon	0.10	+0.02
Chromium	0.1 to 0.2	±0.02
Chromium	5.5 to 6.5	±0.30
Cobalt	0.2 to 0.8	±0.05
Hydrogen	0.02	+0.002
Iron	0.80	+0.15
Iron	1.2 to 1.8	±0.20
Molybdenum	0.2 to 0.4	±0.03
Molybdenum	0.6 to 1.2	±0.15
Molybdenum	1.5 to 4.5	±0.20
Molybdenum	14.0 to 16.0	±0.50
Nickel	0.3 to 0.9	±0.05
Niobium	2.2 to 3.2	±0.15
Niobium	>30	±0.50
Nitrogen	0.05	+0.02
Oxygen	0.30	+0.03
Oxygen	0.31 to 0.40	±0.04
Palladium	0.01 to 0.02	±0.002
Palladium	0.04 to 0.08	±0.005
Palladium	0.12 to 0.25	±0.02
Ruthenium	0.02 to 0.04	±0.005
Ruthenium	0.04 to 0.06	±0.005
Ruthenium	0.08 to 0.14	±0.01
Silicon	0.06 to 0.50	±0.02
Tin	0.6 to 3.0	±0.15
Vanadium	0.6 to 4.5	±0.15
Vanadium	7.5 to 8.5	±0.40
Zirconium	0.6 to 1.4	±0.15
Residuals ^A (each)	0.15	+0.02

^A A residual is an element present in a metal or alloy in small quantities and is inherent to the manufacturing process but not added intentionally. In titanium these elements include aluminum, vanadium, tin, iron, chromium, molybdenum, niobium, zirconium, hafnium, bismuth, ruthenium, palladium, yttrium, copper, silicon, cobalt, tantalum, nickel, boron, manganese and tungsten.

16.1.4 Coiled sheet and strip shall be marked near the outside end of the coil.

16.2 *Packaging*—Unless otherwise specified, material purchased under this specification may be packaged for shipment either by boxing, crating, single boarding, burlapping, or with no protection in accordance with the manufacturer's standard practice.

17. Keywords

17.1 plate; sheet; strip; titanium; titanium alloys

TABLE 10 Permissible Variations in Width^A of Titanium Strip

Specified Thickness, in. (mm)	Permissible Variations from Specified Width, plus and minus, for Widths Given, in. (mm)					
	Under ½ to ¾ (12.70 to 4.76), incl	½ to 6 (12.70 to 152.40), incl	Over 6 to 9 (152.40 to 228.60), incl	Over 9 to 12 (228.60 to 304.80), incl	Over 12 to 20 (304.80 to 508.0), incl	Over 20 to 24 (508.0 to 609.6), excl
Under ¾ to 0.161 (4.76 to 4.09), incl	...	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)	0.031 (0.79)	0.031 (0.79)
0.160 to 0.100 (4.06 to 2.54), incl	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.016 (0.41)	0.020 (0.51)	0.020 (0.51)
0.099 to 0.069 (2.51 to 1.75), incl	0.008 (0.20)	0.008 (0.20)	0.010 (0.25)	0.010 (0.25)	0.016 (0.41)	0.020 (0.51)
0.068 (1.73) and under	0.005 (0.13)	0.005 (0.13)	0.005 (0.13)	0.010 (0.25)	0.016 (0.41)	0.020 (0.51)

^A These tolerances are applicable for a standard No. 3 edge.

TABLE 11 Permissible Variations in Length of Titanium Strip

Specified Length, ft (m)	Permissible Variations in Length, in. (mm)
To 5 (1.524), incl	+¾ (+9.52), –0
Over 5 to 10 (1.524 to 3.048), incl	+½ (+12.70), –0
Over 10 to 20 (3.048 to 6.096), incl	+¾ (+15.88), –0

TABLE 12 Permissible Variations in Thickness of Titanium Strip^A

Specified Thickness, in. (mm)	Permissible Variations from Specified Thickness, plus and minus, for Widths Given, in. (mm)							
	Under 1 to ¾ (25.4 to 4.76), incl	Under 3 to 1 (76.2 to 25.4), incl	3 to 6 (76.2 to 152.4), incl	Over 6 to 9 (152.4 to 228.6), incl	Over 9 to 12 (228.6 to 304.8), incl	Over 12 to 16 (304.8 to 406.4), incl	Over 16 to 20 (406.4 to 508.0), incl	Over 20 to 24 (508.0 to 609.6), incl
Under ¾ to 0.161 (4.76 to 4.09), incl	0.002 (0.05)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)	0.004 (0.10)	0.005 (0.13)	0.006 (0.16)	0.006 (0.16)
0.160 to 0.100 (4.06 to 2.54), incl	0.002 (0.05)	0.002 (0.05)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)	0.004 (0.10)	0.005 (0.13)	0.005 (0.13)
0.099 to 0.069 (2.51 to 1.75), incl	0.002 (0.05)	0.002 (0.05)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)	0.004 (0.10)
0.068 to 0.050 (1.73 to 1.27), incl	0.002 (0.05)	0.002 (0.05)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)
0.049 to 0.040 (1.24 to 1.02), incl	0.002 (0.05)	0.002 (0.05)	0.0025 (0.06)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.004 (0.10)	0.004 (0.10)
0.039 to 0.035 (0.99 to 0.89), incl	0.002 (0.05)	0.002 (0.05)	0.0025 (0.06)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)	0.003 (0.08)
0.034 to 0.029 (0.86 to 0.74), incl	0.0015 (0.04)	0.0015 (0.04)	0.002 (0.05)	0.0025 (0.06)	0.0025 (0.06)	0.0025 (0.06)	0.003 (0.08)	0.003 (0.08)
0.028 to 0.026 (0.71 to 0.66), incl	0.001 (0.03)	0.0015 (0.04)	0.0015 (0.04)	0.002 (0.05)	0.002 (0.05)	0.002 (0.05)	0.0025 (0.06)	0.003 (0.08)
0.025 to 0.020 (0.64 to 0.51), incl	0.001 (0.03)	0.001 (0.03)	0.0015 (0.04)	0.002 (0.05)	0.002 (0.05)	0.002 (0.05)	0.0025 (0.06)	0.0025 (0.06)
0.019 to 0.017 (0.48 to 0.43), incl	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.0015 (0.04)	0.0015 (0.04)	0.002 (0.05)	0.002 (0.05)	0.002 (0.05)
0.016 to 0.013 (0.41 to 0.33), incl	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.0015 (0.04)	0.0015 (0.04)	0.0015 (0.04)	0.002 (0.05)	0.002 (0.05)
0.012 (0.30)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.0015 (0.04)	0.0015 (0.04)	0.0015 (0.04)
0.011 (0.28)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.0015 (0.04)	0.0015 (0.04)	0.0015 (0.04)
0.010 ^B (0.25)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)	0.001 (0.03)		0.001 (0.03)	0.0015 (0.04)	0.0015 (0.04)

^A Thickness measurements are taken ¾ in. (9.5 mm) from the edge of the strip, except that on widths less than 1 in. (25.4 mm) the tolerances given are applicable for measurements at all locations.

^B For thicknesses under 0.010 in. (0.25 mm), in widths to 16 in. (406 mm) a tolerance of ±10 % of the thickness shall apply. In widths over 16 to 23½ in. (406 to 608 mm), incl, a tolerance of ±15 % of the thickness shall apply.

TABLE 13 Permissible Variations in Weight of Titanium Strip

The actual shipping weight of any one item of an ordered thickness and width in any finish may exceed estimated weight by as much as 10 %.

TABLE 14 Permissible Variations in Width and Length^A of Titanium Plate, Rectangular, Sheared

Specified Length, in. (mm)	Specified Width, in. (mm)	Permissible Variations Over Specified Dimension for Thicknesses Given, in. (mm)					
		Under 3/8 (9.52)		3/8 to 5/8 (9.52 to 15.88), excl		5/8 (15.88) and over	
		Width	Length	Width	Length	Width	Length
Under 120 (3048)	Under 60 (1524)	3/8 (9.52)	1/2 (12.70)	7/16 (11.11)	5/8 (15.88)	1/2 (12.70)	3/4 (19.05)
	60 to 84 (1524 to 2134), excl	7/16 (11.11)	5/8 (15.88)	1/2 (12.70)	11/16 (17.46)	5/8 (15.88)	7/8 (22.22)
	84 to 108 (2134 to 2743), excl	1/2 (12.70)	3/4 (19.05)	5/8 (15.88)	7/8 (22.22)	3/4 (19.05)	1 (25.40)
	108 (2743) or over	5/8 (15.88)	7/8 (22.22)	3/4 (19.05)	1 (25.40)	7/8 (22.22)	1 1/8 (28.58)
120 to 240 (3048 to 6096), excl	Under 60 (1524)	3/8 (9.52)	3/4 (19.05)	1/2 (12.70)	7/8 (22.22)	5/8 (15.88)	1 (25.40)
	60 to 84 (1524 to 2134), excl	1/2 (12.70)	3/4 (19.05)	5/8 (15.88)	7/8 (22.22)	3/4 (19.05)	1 (25.40)
	84 to 108 (2134 to 2743), excl	9/16 (14.29)	7/8 (22.22)	11/16 (17.46)	1 1/16 (23.81)	1 3/16 (20.64)	1 1/8 (28.58)
	108 (2743) or over	5/8 (15.88)	1 (25.40)	3/4 (19.05)	1 1/8 (28.58)	7/8 (22.22)	1 1/4 (31.75)
240 to 360 (6096 to 9144), excl	Under 60 (1524)	3/8 (9.52)	1 (25.40)	1/2 (12.70)	1 1/8 (28.58)	5/8 (15.88)	1 1/4 (31.75)
	60 to 84 (1524 to 2134), excl	1/2 (12.70)	1 (25.40)	5/8 (15.88)	1 1/8 (28.58)	3/4 (19.05)	1 1/4 (31.75)
	84 to 108 (2134 to 2743), excl	9/16 (14.29)	1 (25.40)	11/16 (17.46)	1 1/8 (28.58)	7/8 (22.22)	1 3/8 (34.92)
	108 (2743) or over	11/16 (17.46)	1 1/8 (28.58)	7/8 (22.22)	1 1/4 (31.75)	1 (25.40)	1 3/8 (34.92)
360 to 480 (9144 to 12192), excl	Under 60 (1524)	7/16 (11.11)	1 1/8 (28.58)	1/2 (12.70)	1 1/4 (31.75)	5/8 (15.88)	1 1/2 (38.10)
	60 to 84 (1524 to 2134), excl	1/2 (12.70)	1 1/4 (31.75)	5/8 (15.88)	1 3/8 (34.92)	3/4 (19.05)	1 1/2 (38.10)
	84 to 108 (2134 to 2743), excl	9/16 (14.29)	1 1/4 (31.75)	3/4 (19.05)	1 3/8 (34.92)	7/8 (22.22)	1 1/2 (38.10)
	108 (2743) or over	3/4 (19.05)	1 3/8 (34.92)	7/8 (22.22)	1 1/2 (38.10)	1 (25.40)	1 5/8 (41.28)
480 to 600 (12192 to 15240), excl	Under 60 (1524)	7/16 (11.11)	1 1/4 (31.75)	1/2 (12.70)	1 1/2 (38.10)	5/8 (15.88)	1 5/8 (41.28)
	60 to 84 (1524 to 2134), excl	1/2 (12.70)	1 3/8 (34.92)	5/8 (15.88)	1 1/2 (38.10)	3/4 (19.05)	1 5/8 (41.28)
	84 to 108 (2134 to 2743), excl	5/8 (15.88)	1 3/8 (34.92)	3/4 (19.05)	1 1/2 (38.10)	7/8 (22.22)	1 5/8 (41.28)
	108 (2743) or over	3/4 (19.05)	1 1/2 (38.10)	7/8 (22.22)	1 5/8 (41.28)	1 (25.40)	1 3/4 (44.45)
600 (15 240) or over	Under 60 (1524)	1/2 (12.70)	1 3/4 (44.45)	5/8 (15.88)	1 7/8 (47.62)	3/4 (19.05)	1 7/8 (47.62)
	60 to 84 (1524 to 2134), excl	5/8 (15.88)	1 3/4 (44.45)	3/4 (19.05)	1 7/8 (47.62)	7/8 (22.22)	1 7/8 (47.62)
	84 to 108 (2134 to 2743), excl	5/8 (15.88)	1 3/4 (44.45)	3/4 (19.05)	1 7/8 (47.62)	7/8 (22.22)	1 7/8 (47.62)
	108 (2743) or over	7/8 (22.22)	1 3/4 (44.45)	1 (25.40)	2 (50.80)	1 1/8 (28.58)	2 1/4 (57.15)

^A The tolerance under the specified width and length is 1/4 in. (6.35 mm).

TABLE 15 Permissible Variations from a Flat Surface for Titanium Plate, Annealed

Specified Thickness, in. (mm)	Permissible Variations from a Flat Surface for Width or Length Given, in. (mm)								
	48 (1219) or Under	48, excl to 60 (1219 to 1524), excl	60 to 72 (1524 to 1829), excl	72 to 84 (1829 to 2134), excl	84 to 96 (2134 to 2438), excl	96 to 108 (2438 to 2743), excl	108 to 120 (2743 to 3048), excl	120 to 144 (3048 to 3658), excl	144 (3658) and Over
3/16 to 1/4 (4.76 to 6.35), excl	3/4 (19.05)	1 1/16 (26.99)	1 1/4 (31.75)	1 3/8 (34.92)	1 5/8 (41.28)	1 5/8 (41.28)	1 7/8 (47.62)	2 (50.8)	2 1/4 (57.15)
1/4 to 3/8 (6.35 to 9.54), excl	11/16 (17.46)	3/4 (19.05)	1 5/16 (23.81)	1 1/8 (28.58)	1 3/8 (34.92)	1 7/16 (36.51)	1 9/16 (36.69)	1 7/8 (47.62)	2 1/8 (53.98)
3/8 to 1/2 (9.54 to 12.70), excl	1/2 (12.70)	9/16 (14.29)	1 1/16 (17.46)	3/4 (19.05)	1 5/16 (23.81)	1 1/8 (28.58)	1 1/4 (31.75)	1 7/16 (36.51)	1 3/4 (44.45)
1/2 to 3/4 (12.70 to 19.05), excl	1/2 (12.70)	9/16 (14.29)	5/8 (15.88)	5/8 (15.88)	1 3/16 (20.64)	1 1/8 (28.58)	1 1/8 (28.58)	1 1/8 (28.58)	1 3/8 (34.92)
3/4 to 1 (19.05 to 25.40), excl	1/2 (12.70)	9/16 (14.29)	5/8 (15.88)	5/8 (15.88)	3/4 (19.05)	1 3/16 (20.64)	1 5/16 (23.81)	1 (25.40)	1 1/8 (28.58)
1 to 1 1/2 (25.40 to 38.10), excl	1/2 (12.70)	9/16 (14.29)	9/16 (14.29)	9/16 (14.29)	11/16 (17.46)	11/16 (17.46)	11/16 (17.46)	3/4 (19.05)	1 (25.40)
Over 1 1/2 to 4 (38.10 to 101.6), excl	3/16 (4.76)	5/16 (7.94)	3/8 (9.54)	7/16 (11.11)	1/2 (12.70)	9/16 (14.29)	5/8 (15.88)	3/4 (19.05)	7/8 (22.22)
Over 4 to 6 (101.6 to 152.4), excl	1/4 (6.35)	3/8 (9.54)	1/2 (12.70)	9/16 (14.29)	5/8 (15.88)	3/4 (19.05)	7/8 (22.22)	1 (25.40)	1 1/8 (28.58)

Note 1—Variations in flatness apply to plates up to 15 ft (4.57 m) in length, or to any 15 ft of longer plates.

Note 2—If the longer dimension is under 36 in. (914 mm) the variation is not greater than 1/4 in. (6.35 mm).

Note 3—The shorter dimension specified is considered the width and the variation in flatness across the width does not exceed the tabular amount for that dimension.

Note 5—The maximum deviation from a flat surface does not customarily exceed the tabular tolerance for the longer dimension specified.

TABLE 16 Permissible Variations in Thickness for Titanium Plate

Specified Thickness, in. (mm)	Width, in. (mm) ^A			
	To 84 (2134), incl	Over 84 (2134) to 120 (3048), incl	Over 120 (3048) to 144 (3658), incl	Over 144 (3658)
	Tolerances Over Specified Thickness, in. (mm) ^B			
0.1875 (4.76) to 0.375 (9.52), excl	0.045 (1.14)	0.050 (1.27)	...	...
0.375 (9.52) to 0.750 (19.05), excl	0.055 (1.40)	0.060 (1.52)	0.075 (1.90)	0.090 (2.29)
0.750 (19.05) to 1.000 (25.40), excl	0.060 (1.52)	0.065 (1.65)	0.085 (2.16)	0.100 (2.54)
1.000 (25.40) to 2.000 (50.80), excl	0.070 (1.78)	0.075 (1.90)	0.095 (2.41)	0.115 (2.92)
2.000 (50.80) to 3.000 (76.20), excl	0.125 (3.18)	0.150 (3.81)	0.175 (4.44)	0.200 (5.08)
3.000 (76.20) to 4.000 (101.6), excl	0.175 (4.44)	0.210 (5.33)	0.245 (6.22)	0.280 (7.11)
4.000 (101.6) to 6.000 (152.4), excl	0.250 (6.35)	0.300 (7.62)	0.350 (8.89)	0.400 (10.16)
6.000 (152.4) to 8.000 (203.2), excl	0.350 (8.89)	0.420 (10.67)	0.490 (12.45)	0.560 (14.22)
8.000 (203.2) to 10.000 (254.0), incl	0.450 (11.43)	0.540 (13.72)	0.630 (16.00)	...

^A Thickness is measured along the longitudinal edges of the plate at least $\frac{3}{8}$ in. (9.52 mm), but not more than 3 in. (76.20 mm), from the edge.

^B For circles, the over thickness tolerances in this table apply to the diameter of the circle corresponding to the width ranges shown. For plates of irregular shape, the over thickness tolerances apply to the greatest width corresponding to the width ranges shown. For plates up to 10 in. (254.0 mm) incl. in thickness, the tolerance under the specified thickness is 0.010 in. (0.25 mm).

SUPPLEMENTARY REQUIREMENTS

These requirements shall apply only when specified in the purchase order, in which event the specified tests shall be made by the manufacturer before shipment of the plates.

S1. Surface Requirement Bend Tests

S1.1 The purpose of this test is to measure the cleanliness or ductility, or both, of the metal surface. Specimens shall be taken from sheet or plate material produced from the same ingot or bloom materials, processed the same way to the same nominal thickness, width and length, produced in one production run or campaign, finished in the same way, and otherwise representative of the material supplied.

S1.2 Four guided- or free-bend tests of sheet or plate material limited to the grades listed in S1.4. Two bends shall be made in the L direction and two in the T direction. Each pair of these bends will place opposite surfaces of the sheet or plate material in tension.

S1.3 The bends are to be made in accordance with Test Method **E290**, using Method 1, Guided Bend Test described in paragraph 3.6, bent through 180°, and allowed to spring back naturally. The bend specimen may be of less than full material thickness; however, the outer surface of the specimen must include the original material surface with no material removal or surface conditioning other than at the rounded corners, and must otherwise be representative of the product as supplied. The width of the bend test specimen shall be at least 5 times the thickness.

S1.4 The bend radius will be such to provide minimum elongation of the outer fibers of the bent specimen at 180° bend as follows:

Applicable Grades	Minimum Elongation	Bend Radius
1, 11, 13, 17, 27	24 %	1.6 × T
2, 2H, 7, 7H, 14, 16, 16H, 26, 26H, 30, 33, 37, 39	20 %	2.0 × T
3, 12, 15, 31, 34†	18 %	2.3 × T
4, 9, 18, 19, 20, 28	15 %	2.8 × T
5, 6, 21, 23, 24, 25, 26, 29, 32, 36, 38	10 %	4.5 × T
35	5 %	10 × T

†Editorially corrected.

S1.5 Criteria for acceptance will be the absence of any cracking or surface separations not originating at the edge of specimen viewed with the unaided eye.

S1.6 The results of the test shall be reported as required by paragraph 10 of Test Method **E290**.

S2. Alternate Yield Strength Maximum

S2.1 Maximum yield strength (0.2 % Offset) of Grade 1, 11, 17, or 27 shall be limited to 40 ksi (275 MPa).

S3. Special Flatness Requirements

S3.1 These requirements apply only for material to be used for explosive cladding.

S3.2 These requirements apply only to Grades 1, 11, 17, and 27 and only in thickness ranging from 0.078 to 0.78 in. (2.0 to 20 mm), inclusive.

S3.3 The overall out-of-flatness shall be no greater than 50 % of that permitted in **Table 15**.

S3.4 Localized out-of-flatness shall be no greater than 0.12 in. (3.0 mm) deviation from a 39 in. (1000 mm) long straight edge when placed at any location on the plate surface. When

the straight edge is placed on a single high point, the maximum deviation from the plate at each end shall be no greater than 0.12 in. (3.0 mm).

SUMMARY OF CHANGES

Committee B10 has identified the location of selected changes to this standard since the last issue (B265-13a(2013)^{e1}) that may impact the use of this standard. (Approved November 1, 2015.)

(1) Hot rolled sheet is defined as new product.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>